

Loss of the magnetism in FeS

Z. Ropka

Center for Solid State Physics, S^{nt} Filip 5, 31-150 Kraków.

R.J. Radwanski

Center for Solid State Physics, S^{nt} Filip 5, 31-150 Kraków,

Institute of Physics, Pedagogical University, 30-084 Kraków, POLAND.

email: sfradwan@cyf-kr.edu.pl

It is argued that the formation of the non-magnetic state of FeS in external pressures above 6.5 GPa is in agreement with the prediction of the quantum atomistic solid-state theory, an extension of the crystal-field theory with the spin-orbit coupling incorporated, and is related with the change of sign of the off-cubic trigonal distortion marked by the change of the c/a ratio from >1.63 (magnetic) to <1.63 (non-magnetic).

Keywords: highly-correlated electron system, crystal field, low-spin state, Fe²⁺ ion, spin-orbit coupling

PACS: 71.70.E, 75.10.D, 75.30.Gw

Receipt date by Phys.Rev.Lett. 29.08.2000

Recently pressure-induced high-spin to low-spin transition has been evidenced in FeS [1]. A pressure of 6.5 GPa destroys the quite strong magnetism of FeS. FeS is an antiferromagnet with the relatively high Neel temperature of 600 K. It has the hexagonal NiAs structure with $a=345$ pm and $c=585$ pm at room temperature [2].

The aim of this Letter is to point out that the loss of magnetism of FeS can be understood within the quantum atomistic solid-state theory (QUASST), an extension of the crystal-field theory with the spin-orbit coupling incorporated, that points out the existence of the discrete atomic-like states in 3d-ion containing compounds associated with the atomic-like states of the highly-correlated 3dⁿ electron system. Within this theory it has been proven that it is

the local symmetry that determines the realization of the low- or high-spin state of the Co^{3+} ion [3-5]. Namely, it has been proven that as the function of the sign of the off-cubic trigonal distortion of the octahedral crystal-field the ground state of the Co^{3+} ion is the magnetic doublet (the elongation along the main diagonal of the octahedron) or the non-magnetic singlet (the stretching).

Exactly such the conditions are realized in FeS. We learned about it when Ref. 2 came to our attention.

The results obtained in Refs 3 and 4 for the Co^{3+} ion are directly applicable to the Fe^{2+} ion as both systems have 6 electrons in the open 3d-shell in the form of the highly-correlated $3d^6$ system. Analyzing the hexagonal NiAs-type structure of FeS one finds that the Fe^{2+} cation in FeS is in the quasi-octahedral site of the S^{2-} anions. For the ideal value c/a of $\frac{2}{3}\sqrt{6} = 1.63$ the surrounding is the exact octahedron. The beauty of the hexagonal NiAs structure relies in a fact that the trigonal off-cubic distortion can be realized without the spoiling of the overall hexagonal symmetry and the distortion direction is along the hexagonal c axis. The macroscopic lattice parameters reflect directly the atomic-scale octahedron. The $c/a > 1.63$ corresponds to the trigonal elongation of the atomic-scale octahedron whereas the trigonal stretching is marked by $c/a < 1.63$.

According to Ref. 2 with the increasing pressure the ratio c/a stays almost constant (~ 1.70) up to 6.5 GPa. At 6.5 GPa it undergoes the abrupt decrease of the lattice parameter c , by 8.5%, and c/a becomes 1.58 only. Hence, during the transition the sign of the off-cubic trigonal distortion changes. The distortion crystal-field parameter B_2^0 , discussed in Refs 3-5, is in the first-order approximation proportional to $B_2^0 \sim (1.633 - c/a)$ (for the $3d^6$ system).

It is worth to add that the non-magnetic state of FeS can be regarded as the state when the Jahn-Teller effect wins the magnetic state. In fact, the non-magnetic state of the Fe^{2+} ion in FeS can be regarded as quite normal owing to the fact that the Fe^{2+} ion is the non-Kramers system ($3d^6$). According to the Jahn-Teller theorem [6] and Kramers theorem the ground state should be a non-magnetic singlet produced by lattice distortions. Thus, it is magnetic Fe^{2+} -ion compounds that should be treated as exceptional. The quite common

magnetism of the Fe compounds is related with the existence of a great number of closely lying localized states at the neighborhood of the ground state. Such the situation helps development of magnetism as we know from rare-earth compounds. The significant number of closely-lying localized states is somehow related to the small value of the intra-atomic spin-orbit coupling in case of 3d ions [7].

In conclusion, we argue that the formation of the non-magnetic state of FeS in external pressures above 6.5 GPa is in agreement with the prediction of the quantum atomistic solid-state theory (an extension of the crystal-field theory with the spin-orbit coupling incorporated) and is related with the change of sign of the off-cubic trigonal distortion marked by the change of the c/a ratio from >1.63 (magnetic) to <1.63 (non-magnetic). The fine electronic structure of FeS in the magnetic state (low pressure) is quite similar to that derived for FeBr₂ [8] with the magnetic doublet ground state. At high pressures the arrangement of the doublet-singlet sequence reverses to the fine electronic structure found in LaCoO₃ [3,5] with the non-magnetic singlet ground state.

E-mail for correspondence: sfradwan@cyf-kr.edu.pl

-
- [1] J.-P.Rueff, C.-C.Kao, V.V.Struzhkin, J.Badro, J.Shu, R.J.Henley and H.K.Mao, Phys.Rev.Lett. 82, 3284 (1999)
 - [2] T.Kamimura, M.Sato, H.Takahashi, N.Mori, H.Yosida and T.Kaneko, J.Magn.Magn.Magn. 104-107, 255 (1992) - this paper came to our attention 29.08.2000.
 - [3] R.J.Radwanski and Z.Ropka, Solid State Commun. 112, 621 (1999); The formation of a non-magnetic state for the d⁶ electronic system, <http://xxx.lanl.gov/abs/cond-mat/9906437>.
 - [4] R.J.Radwanski and Z.Ropka, Local off-cubic distortion the cause for the low- and high-spin states of the Co³⁺ ion, <http://xxx.lanl.gov/abs/cond-mat/0006269>.
 - [5] R.J.Radwanski and Z.Ropka, Physica B 281&282, 507 (2000).

- [6] it is worth to point out that the Jahn-Teller theorem for 3d-ion compounds should be considered within the spin-orbital space (not in the orbital space only as is commonly made), see Z.Ropka and R.J.Radwanski, Jahn-Teller theorem for the 3d magnetic ions, <http://xxx.lanl.gov/abs/cond-mat/0006231>.
- [7] R.J.Radwanski and Z.Ropka, Relativistic effects in the electronic structure for the 3d paramagnetic ions, <http://xxx.lanl.gov/abs/cond-mat/9907140>.
- [8] Z.Ropka, R.Michalski and R.J.Radwanski, Electronic and magnetic properties of FeBr₂, <http://xxx.lanl.gov/abs/cond-mat/0005502>.